

**PRODUCT DESCRIPTION**

PLASTIVO 250 is a waterproof coating featuring high elasticity and versatility of use to waterproof surfaces subject to positive and negative hydrostatic pressure.

**PRODUCT APPLICATION**

Positive and negative hydrostatic pressure waterproofing of structures made of concrete, cement blocks or mixed masonry, previously levelled with suitable VOLTECO mortars, affected by moderate settlements and/or movements.

Particularly suitable for:

- Walls and foundations slabs and reinforced cement floors in garages, cellars, underground structures in general
- Slabs and structures exposed to contact with water
- Substrates in general, also lightened with expanded clay
- Tanks, canals, swimming pools and structures designed to contain water, including drinking water

ADVANTAGES

- High flexibility
- Suitable for contact with drinking water
- Suitable for contact with purifier water and domestic wastewater
- Protects concrete surfaces from CO₂ (Carbonation)
- Excellent workability and quick application
- Complete waterproofing cycle within one day
- Good water vapour permeability
- Adheres to different types of surfaces (concrete, brickwork, brick, gypsum board, plastic, metal, ceramic, polystyrene, wood, other)
- Reduced environmental impact thanks to the use of raw materials with low carbon footprint and obtained from recycling processes
- Reduced volatile organic compound (VOC) emissions
- The product helps earning points for LEED certification
- Resistant to U.V. radiation

PREPARATION AND APPLICATION The preparation and installation data refer to normal environmental conditions (temperature +20°C; relative humidity 60%).

Preparing the surfaces

Verify the structure suitability for the hydrostatic loads; if intended to contain water, perform a preload test.

Remove any dirt, oil, paint and any material or deposit that could compromise adhesion of PLASTIVO by pressure blasting, sandblasting or bush-hammering lightly.

The surface that is to be treated must be solid and perfectly clean from cement laitance.

Repair the surface with suitable VOLTECO mortar if the surfaces are very uneven, have gravel nests or



in the case of mixed masonry.

If the surfaces are old and/or dusty or partially soaked with water, apply PROFIX 30, PROFIX 60 or PROFIX 80 primer (see the relevant technical data sheets) with a roller, a brush or by spray.

Preparation of elements of discontinuity on reinforced concrete structures (positive hydrostatic pressure)

- **CONSTRUCTION JOINTS** Fill the construction joint between the bed and vertical wall by executing a 3x3 cm fillet with SPIDY 15 quick mortar (see relevant technical data sheet) and, if WT gaskets were not used, seal all horizontal and vertical joints by means of BI FLEX System (see relevant technical data sheet) even where the fillet is present
- **SPACERS** Remove the spacers on both sides of the wall and plaster with SPIDY 15 rapid-setting mortar
- **PENETRATIONS** Seal all penetrations (pipes, lighting points, etc.) by means of AKTI-VO 201 mastic (see relevant data sheet)
- **JOINTS and CRACKS** Fill any structural joints and marked cracks by means of BI FLEX System

Preparation of elements of discontinuity on reinforced concrete structures (negative hydrostatic pressure and for all cases of water retaining structures)

- **WATER FLOWS** Seal any water inflow with TAP 3/I-PLUG quick-setting mortar (see the related technical data sheet)
- **CONSTRUCTION JOINTS** Seal all construction joints with BI FLEX System
- **JOINTS and CRACKS** Seal any structural joints and cracks by means of BI FLEX System
- **PENETRATIONS** Seal all penetrations, including spacers, pipes and lighting points by means of AKTI-VO 201 mastic

Preparing the mixture

Stir the liquid component in its container, then pour it into a bucket.

Gradually add the powder while continuing to stir.

Use a whip-fitted drill with a low rpm and mix for approx. 3-5 minutes.

The mixture must be smooth and free of lumps.

Application

If PROFIX primer has not been applied, wet the surfaces making sure no surface water is formed.

PLASTIVO 250 must be applied in two layers with a VOLTECO ROLLER, brush, squeegee or spatula.

Apply the first layer of PLASTIVO 250 on the surface, approximately 1 mm thick (average consumption: 1.8÷2 kg/m²), making sure the product penetrates well into the substrate, in order to obtain uniform coverage.

If the roller/brush tends to drag the product, do not add water, dampen the surface instead.

The second layer, approximately 1 mm thick (average consumption: 1.7÷2 kg/m²) must be applied after at least 6 hours.

In any case, it is recommended to only apply the second coat when the previous one is dry and hardened.

The average thickness of approx. 1 mm per layer must continue to be applied according to the previous layers in applications that require a thickness greater than the standard 2 mm.

Sprayed application

The product can also be applied with a pneumatic pump or plastering machine with levelling lance, taking care to apply a certain amount of pressure with a spatula until a compact surface is obtained (for further information contact Volteco's Technical Service).

FLEXONET or XNET reinforcement mesh

To improve elastic performance, in case of application in positive pressure (ex. crazing with dynamic behaviour, in roof top pools and structures that are potentially subject to cracking), it is advisable to place the FLEXONET or XNET (see the relative technical data sheets) mesh "fresh on fresh" on the 1st coat, pressing it down with a metal spatula until it is completely embedded.

The edges of adjacent sheets must overlap by 10 cm.

At the connection points between horizontal and vertical surfaces, and in any case at the BI FLEX System placed in the construction joints and joints, interrupt the mesh by overlapping it at the edge of the tape.

Curing

When waterproofing foundation walls, let it cure for at least 24 hours after application before backfilling.

When coating the waterproofing with any type of protective layer or finish (ceramic coating, protective



screed, plaster, cement-based levelling compound, plastic drainage, etc.), let it cure at least 3 days after application.

When waterproofing structures intended to contain water, allow a curing phase of at least 7 days once the product is applied.

When used in contact with drinking water, wash the surfaces with running water before filling the container.

The curing times can be longer in the presence of a low temperature, high humidity or premature contact with water.

Finishing

Depending on the intended use, the product can be finished either by painting with CRYSTAL POOL or with BI MORTAR RASO SEAL cement-based coating (see method and stratigraphy in the relevant technical data sheets) or with ceramic.

Ceramics must be laid with a large grout gap and C2-type adhesive (preferably with an S1 and S2 deformation class).

Line grouting works must be carried out with CG2 class cement-based grouting mortars.

When applied indoors, it is recommended to coat the walls with the macroporous CALIBRO as an anti-condensation layer.

It is also possible to complete the finish with X-LIME (see relative data sheet).



References available at www.volteco.com

CONSUMPTION AND YIELD

3.5÷4 kg/m² depending on the roughness of the surface.

PACKAGING AND STORAGE

PLASTIVO 250 is supplied in 20.6 kg packages (14 kg in powder + 6.6 kg in liquid).

The product must be stored in a dry place without being exposed to frost and heat (maximum temperature: 40°C) or direct exposure to the sun before being applied.

WARNINGS - IMPORTANT NOTES

The product is not a vapour barrier.

Do not apply PLASTIVO 250 on water-soaked surfaces; first seal with TAP 3/I-PLUG hydraulic mortar.

Do not add water to the mixture or alter the mixing ratio.

Do not apply the product if the temperature is higher than +30°C or lower than +5°C or if it is expected to drop below this temperature within 24 hours.

If more than 28 days have passed since the second coating, an additional layer must be applied to ensure the subsequent coating adheres well.

When installation is performed in closed and poorly ventilated environments, it is recommended to use forced ventilation during installation itself and throughout the curing process.

Significant condensation may occur in environments with poor ventilation or high humidity.

If waterproofing earth retaining walls, it is recommended to protect PLASTIVO 250 with a non-woven application of at least 300 g/m² in weight before backfilling.

Do not use PLASTIVO 250 for layers thicker than 1.5 mm.

Protect wet product from rain.

Finishing with solvent-based paints may degrade PLASTIVO 250, check its compatibility via preliminary tests.

PHYSICAL AND TECHNICAL SPECIFICATIONS

Specification	Values
Appearance	Grey powder - white latex
Workability time at +20 °C	20'



Specification	Values			
Working temperature	-5 °C to +50 °C			
Maximum aggregate size	0.7 mm			
Specific weight	> 1.6 kg/l			
Liquid/powder mixing ratio	47/100			
Feature	Test method	Performance requirements UNI EN 1504-2	Declared performance (*)	Certified performance (**)
Bond strength	UNI EN 1542	≥ 0.8 MPa	≥ 0.8 MPa	1.08 MPa
Resistance to accelerated ageing	UNI EN 1062-11	No swelling	-	Fulfilled requisite
Capillary absorption	UNI EN 1062-3	≤ 0.1 kg*m ⁻² *h ^{-0.5}	≤ 0.05 kg*m ⁻² *h ^{-0.5}	0.01 kg*m ⁻² *h ^{-0.5}
Water vapour permeability (equivalent thickness: Sd)	UNI EN 7783-2	Class 2 5 m < Sd ≤ 50 m	-	Sd 14.76 m
Permeability to CO ₂ (equivalent thickness Sd)	UNI EN 1062-6	Sd > 50 m	-	Sd 113 m
Crack Bridging Ability	UNI EN 1062-7 (static method)	A2 > 0.25 mm A3 > 0.50 mm A4 > 1,25 mm A5 > 2.50 mm	-	Class A4 1.6 mm
Crack Bridging Ability (product + Flexonet mesh)	UNI EN 1062-7 (static method)	A2 > 0.25 mm A3 > 0.50 mm A4 > 1,25 mm A5 > 2.50 mm	-	Class A5 3.6 mm
Crack Bridging Ability (product + Xnet mesh)	UNI EN 1062-7 (static method)	A2 > 0.25 mm A3 > 0.50 mm A4 > 1,25 mm A5 > 2.50 mm	-	Class A5 2.8 mm
Thermal compatibility Part 1 (adhesion after 50 un/freezing cycles)	UNI EN 13687-1	≥ 0.8 MPa	-	1.12 MPa
Resistance to severe chemical attack	UNI EN 13529	-	-	Reduction in hardness (Shore A): < 2%
Reaction to fire	UNI EN 13501-1	Classification	-	Class F
Feature	Test method	Performance requirements	Declared performance (*)	
Crack Bridging Ability (+23 °C)	UNI EN 14891 Met. A.8.2	> 0.75 mm	> 1 mm	
Crack Bridging Ability (-5 °C)	UNI EN 14891 Met. A.8.3	> 0.75 mm	> 1 mm	
Crack Bridging Ability (+23 °C) (product + Flexonet mesh)	UNI EN 14891 Met. A.8.2	> 0.75 mm	> 2 mm	
Crack Bridging Ability (-5 °C) (product + Flexonet mesh)	UNI EN 14891 Met. A.8.3	> 0.75 mm	> 2 mm	
Crack Bridging Ability (+23 °C) (product + Xnet mesh)	UNI EN 14891 Met. A.8.2	> 0.75 mm	> 2 mm	
Crack Bridging Ability (-5 °C) (product + Xnet mesh)	UNI EN 14891 Met. A.8.3	> 0.75 mm	> 2 mm	
Initial adhesion	UNI EN 14891 Met. A.6.2	> 0.5 N/mm ²	1 N/mm ²	
Adhesion after immersion in water	UNI EN 14891 Met. A.6.3	> 0.5 N/mm ²	0.7 N/mm ²	
Adhesion after heat application	UNI EN 14891 Met. A.6.5	> 0.5 N/mm ²	0.7 N/mm ²	
Adhesion after un/freezing cycles	UNI EN 14891 Met. A.6.6	> 0.5 N/mm ²	0.7 N/mm ²	
Tensile adhesion strength after contact with chlorinated water	UNI EN 14891 Met. A.6.7	> 0.5 N/mm ²	0.8 N/mm ²	
Adhesion after immersion in alkaline water	UNI EN 14891 Met. A.6.9	> 0.5 N/mm ²	0.7 N/mm ²	
Water impermeability	UNI EN 14891 Met. A.7	150 KPa	150 KPa	
Feature	Certifying body	Test method	Certified performance (**)	
Impermeability in negative pressure (concrete structure Water/Concrete: 0.7)	IMM SA (Switzerland)	UNI EN 12390-8	5 Bar: no passage	
VOC content	Eurofins 392-2015-00130901	Directive 42/2004/EC ISO 11890-2 ASTM D 6886-12	1.5 g/l	
Feature	Certification			
Suitable for contact with drinking water (Italian Ministerial Decree 174 of	ELLETIPI Srl Report n° 28754/15			



Feature	Certification
06/04/2004: global transfer)	
Suitable for use with water in domestic waste water purifiers	ELLETIPI Srl Report n° 14420/15
Tanks and water reserves waterproofing approval	SOCOTEC FRANCE S.A. Report (ETN) n° 240368080000031 (30/06/2029)



The quoted data are obtained in a laboratory at +20 °C and 60% RH.

* Performance thresholds guaranteed by VOLTECO

** Performance values certified by accredited third parties

SAFETY

Refer to the related Safety Data Sheet.

 VOLTECO S.p.a Via delle Industrie, 47 - 31050 Ponzano Veneto (I)	 VOLTECO S.p.a Via delle Industrie, 47 - 31050 Ponzano Veneto (I)
10 DOP 0003 EN 1504-2:2005 1370-CPR-1299 PLASTIVO 250 Protection systems of the concrete surface. Coating against the risks of penetration (PI), humidity control (MC) and increased resistivity (IR)	15 DOP 0023 EN 14891:2012 PLASTIVO 250 Two-component liquid waterproofing product modified with polymer (CM 01P) for outdoor applications and in pools under ceramic tiles(applied with class C2 adhesive in compliance with EN 12004)
Reaction to fire: Class F Water vapour permeability: Class I Carbon dioxide permeability: $S_d \geq 50$ m Capillary absorption and permeability to water: $< 0.1 \text{ kg} \cdot \text{m}^{-2} \cdot \text{h}^{0.5}$ Adhesion: $\geq 0,8 \text{ N/mm}^2$ Thermal compatibility: - Part 1: Un/freezing cycles: $\geq 0.8 \text{ N/mm}^2$ Crack bridging properties (method A): Class A4 Performance after exposure to the action of artificial atmospheric agents: Test passed Methods of conditioning before testing (7 days at 70°C): NPD Linear shrinkage: NPD Coefficient of thermal expansion: NPD Cross cut: NPD Slip resistance: NPD Antistatic behavior: NPD Adhesion on wet concrete: NPD Hazardous substances: See SDS	Initial tensile adhesion strenght: $\geq 0,5 \text{ N/mm}^2$ Tensile adhesion strength after water contact: $\geq 0,5 \text{ N/mm}^2$ Tensile adhesion strength after heat ageing: $\geq 0,5 \text{ N/mm}^2$ Tensile adhesion strength after freeze-thaw cycles: $\geq 0,5 \text{ N/mm}^2$ Tensile adhesion strength after contact with lime water: $\geq 0,5 \text{ N/mm}^2$ Tensile bond strength after immersion in lime water: $\geq 0,5 \text{ N/mm}^2$ Water impermeabiiti: No penetration and ≤ 20 g weight gain Crack bridging ability under standard conditions (23°C): $\geq 0,75 \text{ mm}$ Crack bridging ability at low temperatures (-5°C): $\geq 0,75 \text{ mm}$ Hazardous substances: See SDS

COPYRIGHT

© Copyright Volteco S.p.A. - All rights reserved.

Information, images and text found in this document are exclusive property of Volteco S.p.A.

They may change anytime without prior notice.

Updated versions of this and other documentation (specification, brochure, other) are on www.volteco.com.

In case of translation text may contain technical and linguistic inaccuracies.

LEGAL NOTES

Note for buyer/installer:

This document prepared by Volteco S.p.A. is provided as an aid and guideline for the buyer/installer.

This does not take into consideration the details of each single operational context, for which Volteco S.p.A. will not be held liable.

This does not change and does not extend the obligations of Volteco S.p.A.

It may vary and the installer is therefore required to update his/her information prior to each application by referring to www.volteco.com.

The above clarifications extend to the pre-post-sales technical/commercial information of the commercial network.