

PROFIX 60

Supply and installation of low-viscosity two-component epoxy primer that penetrates deep into the porosity of the surfaces. Suited for the preparation of cement-based surfaces in general, also in the presence of humidity. Also recommended as a strengthening product for cement-based screeds with loose surface parts.

The product must be used for the preparation of cementitious substrates in the presence of humidity (maximum value 8%).

The material must have the following characteristics:

Specification	Values
Mixing ratio	Component A : Component B = 1 : 0.5
Viscosity (+20 °C, \neq 2-20 rpm)	< 1500 mPa • s
Residual humidity on the surface	maximum value 8%
Adhesion to the concrete	> 2 N/mm ² (surface failure)

as well as Profix 60 Volteco or a product with equal or superior characteristics.

The technical data must be supported by test certification issued by an accredited official laboratory and / or be subjected to quality control according to ISO 9001.

For further details on the individual products and installation specifications, refer to the relevant technical data sheets which can be downloaded in the updated version on the website www.volteco.com.