



AQUASCUD SYSTEM 430



FLEXIBLE LIQUID SYSTEMS



PRODUCT DESCRIPTION

AQUASCUD System 430 is a waterproofing system, offering a definitive solution and without having to resort to demolition, for balconies, terraces, roof decks and all flat surfaces, even with flooring installed.

It is a waterproof protective shield against possible causes of infiltration.

Quick, practical and extremely flexible, it is a definitive solution to cutting costs and inconvenience. AQUASCUD System 430 consists of:

- AQUASCUD 430, impermeabilizzante bicomponente flessibile;
- AQUASCUD BASIC: elasticised microporous water-repellent polypropylene membrane, which is roughened thanks to special processing, allowing perfect adhesion to the waterproof coating;
- AQUASCUD JOIN, elasticised staff bead;
- AQUASCUD JOIN BT, adhesive staff bead;
- BI FLEX SYSTEM, elastic tape with epoxy adhesive;
- AQUASCUD LINE, a draining gutter profile to finish and protect flooring edges

PRODUCT APPLICATION

- Waterproofing of flat roofs, balconies, terraces and sloped floors, with flooring already installed, with waterproofing surface that can remain exposed protected by coatings (tiles, concrete floors, green roofs, etc.)
- Substrates in general, also lightened with expanded clay

ADVANTAGES

- It maintains deformability to -20°C
- For waterproofing without demolition.
- Resistant to U.V. radiation
- Low environmental impact thanks to reduced CO₂ emissions, very low Volatile Organic Compound emissions (VOC), components obtained from recycling processes
- Definitive intervention with a thickness of just 3 mm
- Excellent adhesion to all cement, masonry, ceramic and marble surfaces
- Excellent protection of screed against the action of un/freezing and efflorescence
- Allows for direct application of the flooring
- The product helps earning points for LEED certification
- Applicable on existing floor and surfaces with micro-cracks
- No demolition and disposal

PREPARATION AND APPLICATION

The preparation and installation data refer to normal environmental conditions (temperature +20°C; relative humidity 60%).

Preparing the surfaces

Remove all dirt and any other material that could compromise adhesion of AQUASCUD.

Restore very irregular surfaces with FLEXOMIX 30 mortar (see the related technical data sheet).

If the surfaces are old or dusty, apply PROFIX 30 primer with a roller, a brush or by spray (see related technical data sheet).

For substrates that are not completely dry but adequately cured, the surface relative humidity must not exceed 5% (measured using a Storch type electric hygrometer).

If the substrate is partially soaked in water, with relative surface humidity between 5% and 10% (measured using a Storch type electric hygrometer), apply BI MORTAR ULTRA SEAL (see relevant technical data sheet).

Preparation of installation parts and set-ups

- **JOINTS** Any deformation joints (expansion and contraction/splitting) and construction joints on the surface must be covered by means of GARVO joint cover strips (see relevant technical data sheet); in case of structural joints, use BI FLEX System (see relevant technical data sheet)

- In case of insulation joints, fill all wall/floor corners by means of AQUASCUD JOIN (see relevant technical data sheet) staff bead, placing the rubber-coated part in contact with the surface using AQUASCUD sealing material. Alternatively, it is possible to use the AQUASCUD JOIN BT adhesive strip (see relevant technical data sheet) laid on a cured AQUASCUD layer. At low-height situations use AQUASCUD JOIN BT or, alternatively, BI MASTIC adhesive mastic (see relevant technical data sheet)

- **DRAINS** Prepare the connections to the drains by using the relative DRAIN MANIFOLD

- **GUTTER** Along the external perimeter, set up the AQUASCUD LINE draining gutter profile and relative special pieces (see relative data sheet) to finish and protect the tiled edge

- **ARMATURA DI RINFORZO ELASTICA** Preparare la membrana AQUASCUD BASIC già pretagliata nelle dimensioni necessarie al fine di essere poi inserita nella prima mano di miscela impermeabilizzante

Preparing the mixture

Stir the liquid component in its container, then pour it into a bucket.

Gradually add the AQUASCUD powder component while continuing to stir; mix for 2÷3 minutes with a whip-fitted drill until the mixture is smooth and free of lumps.

Application

Apply the first thick layer of AQUASCUD 430 on the surface, a minimum thickness of 1÷1.5 mm using a special 3.5 mm NOTCHED FLOAT or the Volteco NOTCHED SQUEEGEE, making sure the product penetrates well into the substrate and covers the surface completely (average consumption: 2÷2.5 kg/m² depending on the flatness of the surface).

Place the AQUASCUD BASIC membrane on the first coat of mixture in the following manner: proceed in sectors, immediately laying out the AQUASCUD BASIC membrane on the fresh AQUASCUD 430 mixture, making it adhere uniformly to the surface by pressing with the Volteco NEEDLE ROLLER.

AQUASCUD BASIC membrane becomes darker when it is rolled on. This indicates correct application and proper impregnation and adhesion.

Overlap the edges of the AQUASCUD BASIC membrane by at least 10 cm and weld them together with the AQUASCUD mixture.

Where the horizontal and vertical surfaces join, make sure the AQUASCUD BASIC membrane adheres to the horizontal edge of the previously laid AQUASCUD JOIN joint band.

Never fold AQUASCUD BASIC vertically, always join it to the AQUASCUD JOIN joint band.

The AQUASCUD BASIC membrane must be interrupted in the centre line of the tape with GARVO or BI FLEX System at the joints treated.

If there is an AQUASCUD LINE gutter profile along the perimeter, overlap AQUASCUD BASIC by at least 6 cm over the profile anchoring flap.

Wait at least 24 hours (ambient temperature +20°C; ambient humidity 60%) before using NOTCHED TROWEL 3.5 mm or NOTCHED SQUEEGEE to apply a second layer, at least 1 mm thick, of the AQUASCUD 430 mixture (average consumption 1.5 kg/m²), being careful to evenly cover the AQUASCUD BASIC membrane.

When fresh, smooth with ROUNDED PLASTERING TROWEL.

It is recommended to apply the second layer of AQUASCUD 430 only when the previous one is completely dry and hardened.

For applications on balconies or on small surfaces (less than approximately 4 m²), it is possible to omit the use of the AQUASCUD BASIC membrane.

Always apply the AQUASCUD BASIC membrane on a substrate with marked cracks.

Finishing

Ceramics must be laid on AQUASCUD System 430 after at least 2 days, with a large grout gap and C2-type adhesive (preferably with an S1 and S2 deformation class).

Line grouting works must be carried out with CG2 class cement-based grouting mortars.

AQUASCUD System 430 can be left exposed if subjected to occasional foot traffic.



References available at www.volteco.com

CONSUMPTION AND YIELD

3.2÷3.5 kg/m² depending on the roughness of the surface.

PACKAGING AND STORAGE

AQUASCUD 430 is supplied in 18 kg packages (12 kg in powder + 6 kg in liquid).

The product must be stored in a dry place without being exposed to frost and heat (at a temperature between +5°C and +30°C) or direct exposure to the sun before being applied.

ACCESSORIES	-
AQUASCUD JOIN	Elasticised staff bead 25 m package
AQUASCUD JOIN BT	Staff bead with adhesive butyl rubber 20 m package
BI FLEX SYSTEM	Elastic tape Packs of 15, 20 or 40 m Epoxy adhesive Packs of 5 or 10 kg
AQUASCUD BASIC	Water-repellent elasticised microporous membrane 30 m ² package
AQUASCUD LINE	Draining profile with gutter (version H.0 and H.10) 13.5 m package

SPECIAL PIECES	-
JOIN BT 90° Corner / JOIN BT 270° Corner	Pre-shaped staff bead, with adhesive butyl rubber 10 pc package
DRAIN/EXHAUST MANIFOLD	Rubber textile element Ø 80 mm and Ø 100 mm 2 pc package
SQUARE GARVO	Rubber textile element 40x40 cm Single package
AQUASCUD CORNER 90°	Corner for AQUASCUD LINE (version H.0 and H.10) Single package
AQUASCUD CORNER 270°	Corner for AQUASCUD LINE (version H.10) Single package
AQUASCUD FIXY	Connecting joints for AQUASCUD LINE (version H.0 and H.10) Single package
APPLICATION TOOLS	-
NEEDLE ROLLER - 7 kg	-
PLASTIVO ROLLER	-
ROUNDED PLASTERING TROWEL	-
NOTCHED TROWEL 3.5 mm	-
NOTCHED SQUEEGEE	-

WARNINGS - IMPORTANT NOTES

Do not add water, cement or aggregates and do not alter the required mixing ratio in any way.

Apply the product within 20 minutes of mixing (room temperature + 20°C; ambient humidity 60%).

Do not use AQUASCUD 430 in thicknesses greater than 2 mm per coat.

To help achieve the minimum thickness in each coat of the product, it is recommended to use the 3.5 mm NOTCHED TROWEL or NOTCHED SQUEEGEE as thickness regulators.

Wait at least 15 days for the substrate to cure under normal conditions when applied on traditional screeds that have just been made.

Do not apply the product if the temperature is higher than +30°C or lower than +5°C or if it is expected to drop below this temperature within 24 hours.

The curing times will be longer in the presence of rain and/or fog and/or a low temperature.

Applying AQUASCUD on surfaces exposed to the sun will drastically reduce the product's workability time.

Applying AQUASCUD on a humid surface that is extensively exposed to the sun can cause the formation of vapour blisters on the surface.

These do not alter the final characteristics of the product.

Vapour blisters can also form if the 2nd layer is applied on the 1st layer if it has not cured enough or is too thin.

Protect wet product from rain.

Humidity in the substrate causes a significant delay in the curing process.

Set-up suitable anti-root protection in the case of roof gardens.

AQUASCUD BASIC can remain free of AQUASCUD protection mixture up to a maximum of 7 days.

Wait at least 2 days before applying any type of protective or finishing layer.

If more than 28 days have passed since the second coating, an additional layer must be applied to ensure the subsequent coating adheres well.

PHYSICAL AND TECHNICAL SPECIFICATIONS

Specification	Values
Appearance	Grey powder - white latex
Working temperature	-20°C +60°C
Liquid/powder mixing ratio	1/2
Workability time at +20°C	20'
Maximum aggregate size	0.7 mm
Specific weight	> 1.6 kg/l

Feature	Test method	Performance requirements	Declared performance
Crack Bridging Ability (+23°C)	UNI EN 14891 Met. A.8.2	> 0.75 mm	> 1 mm
Crack Bridging Ability (-20°C)	UNI EN 14891 Met. A.8.3	> 0.75 mm	> 1 mm
Crack Bridging Ability (+23°C)(with Aquascud Basic)	UNI EN 14891 Met. A.8.2	> 0.75 mm	> 2 mm
Crack Bridging Ability (-20°C)(with Aquascud Basic)	UNI EN 14891 Met. A.8.3	> 0.75 mm	> 2 mm
Initial adhesion	UNI EN 14891 Met. A.6.2	> 0.5 N/mm ²	> 0.5 N/mm ²
Adhesion after immersion in water	UNI EN 14891 Met. A.6.3	> 0.5 N/mm ²	> 0.5 N/mm ²
Adhesion after heat application	UNI EN 14891 Met. A.6.5	> 0.5 N/mm ²	> 0.7 N/mm ²
Adhesion after un/freezing cycles	UNI EN 14891 Met. A.6.6	> 0.5 N/mm ²	> 0.5 N/mm ²
Adhesion after immersion in alkaline water	UNI EN 14891 Met. A.6.9	> 0.5 N/mm ²	> 0.5 N/mm ²
Water impermeability	UNI EN 14891 Met. A.7	150 KPa	150 KPa

Parameters subject to company Quality Control	Values AQUASCUD BASIC	Values AQUASCUD JOIN
Water impermeability	-	No passage up to 100 kPa
Elongation at breaking point	> 40%	> 20%
Resistance at breaking point	> 0.6 kN/m	> 267 N/5 cm

Feature	Test method	Certifying body	Values (g/l)
VOC content	Directive 42/2004/EC ISO 11890-2 ASTM D 6886-12	Eurofins 392-2015-00130902	2.7

Initial requirements UNI 11928-1:2023

Feature	Test method	Performance requirements	Declared performance
Reaction to fire	UNI EN 13501-1	F	F
Watertightness (water passage with 60 KPa)	UNI EN 1928	No passage	No passage

Feature	Test method	Performance requirements	Declared performance
Water vapour transmission properties	UNI EN ISO 7789	Class	Class I
Direct tensile adhesion, concrete type MC (0.40)	UNI EN 1542	≥ 0.5 N/mm ²	≥ 0.8 N/mm ²
Impact resistance	UNI EN 6272-1	Class	Class III
Static punching	UNI EN 12730	≥ 50 N	≥ 50 N
Dynamic crack bridging (23 °C)	UNI EN 1062-7	Class B2	Class B4.1
Dynamic crack bridging at low temperatures (-20 °C)	UNI EN 1062-7	Class B1	Class B3.2
Slipping resistance	UNI EN 13036-4	Class	Class III
Capillary absorption	UNI EN 1062-1	$W \leq 0.1 \text{ Kg/m}^2 \cdot \text{h}^{-0.5}$	$W \leq 0.1 \text{ Kg/m}^2 \cdot \text{h}^{-0.5}$

Durability UNI 11928-1:2023

Feature	Test method	Performance requirements	Declared performance
Heat ageing resistance 7 days at 70±3 °C (Watertightness)	point 4.1 of EN 1062-11:2003	No passage	No passage
Acceptance criteria after exposure	UNI EN ISO 4628-2 UNI EN ISO 4628-4 UNI EN ISO 4628-5	No swelling No cracking No spalling	No swelling No cracking No spalling
Hazardous substances			See safety data sheets
Frost/thaw Without thawing salts 20 cycles (Adhesion to substrate)	UNI EN 13687-3	≥ 0.5 N/mm ²	≥ 1,0 N/mm ²
Acceptance criteria after exposure	UNI EN ISO 4628-2 UNI EN ISO 4628-4 UNI EN ISO 4628-5	No swelling No cracking No spalling	No swelling No cracking No spalling
UV (400 MJ/m ² , 2460 hours) and Spray (492 hours)	UNI EN ISO 4892-3		
Acceptance criteria after exposure	UNI EN ISO 4628-2 UNI EN ISO 4628-4 UNI EN ISO 4628-5	No swelling No cracking No spalling	No swelling No cracking No spalling
Hazardous substances			See safety data sheets

The quoted data are obtained in a laboratory at +20 °C and 60% RH.

WATCH VIDEOS AND INSIGHTS

Safety Data Sheets


Declaration of performance

Specifications

Technical drawings and BIM

EPD Declaration

YouTube Video



SAFETY

Refer to the related Safety Data Sheet.

CE	VOLTECO S.p.a Via delle Industrie, 47 - 31050 Ponzano Veneto (I)
18 0031-CPR-2018/10/09 EN 14891:2012 AQUASCUD 430	
Two-component liquid waterproofing product modified with polymer (CM 02) for outdoor applications under ceramic tiles (applied with class C2 adhesive in compliance with EN 12004)	
Initial tensile adhesion strength: $\geq 0,5 \text{ N/mm}^2$ Tensile adhesion strength after water contact: $\geq 0,5 \text{ N/mm}^2$ Tensile adhesion strength after heat ageing: $\geq 0,5 \text{ N/mm}^2$ Tensile adhesion strength after freeze-thaw cycles: $\geq 0,5 \text{ N/mm}^2$ Tensile adhesion strength after contact with lime water: $\geq 0,5 \text{ N/mm}^2$ Water impermeability: No penetration and $\leq 20 \text{ g}$ weight gain Crack bridging ability under standard conditions (23°C): $\geq 0,75 \text{ mm}$ Crack bridging ability at low temperatures (-20°C): $\geq 0,75 \text{ mm}$ Hazardous substances: See SDS	

COPYRIGHT

© Copyright Volteco S.p.A. - All rights reserved.

Information, images and text found in this document are exclusive property of Volteco S.p.A.

They may change anytime without prior notice.

Updated versions of this and other documentation (specification, brochure, other) are on www.volteco.com.

In case of translation text may contain technical and linguistic inaccuracies.

LEGAL NOTES

Note for buyer/installer:

This document prepared by Volteco S.p.A. is provided as an aid and guideline for the buyer/installer.

This does not take into consideration the details of each single operational context, for which Volteco S.p.A. will not be held liable.

This does not change and does not extend the obligations of Volteco S.p.A.

It may vary and the installer is therefore required to update his/her information prior to each application by referring to www.volteco.com.

The above clarifications extend to the pre-post-sales technical/commercial information of the commercial network.