

BI MORTAR PLASTER SEAL

Supply and installation of multifunctional waterproof fiber-reinforced plaster applied in two coats, with a minimum thickness of 1.5 cm up to 4 cm depending on the type of use.

The product must be used for:

- For underground structures made of either concrete or mixed material
- To waterproof skirting at the foot of the plaster
- To repair diaphragms with a reinforcement mesh being interlaid

The material must have the following characteristics:

EC Certification according to EN 1504-3:2006

Specification		Test method	Values
Specific weight			> 1.9 kg/l
Compressive strength after 28 days		UNI EN 196-1	> 40.2 MPa
Flexural strength after 1 day after 7 days after 28 days		UNI EN 196-1	> 2.5 MPa > 5.0 MPa > 6.5 MPa
Adhesion to the concrete		UNI EN 1542	2.7 MPa
Compressive modulus of elasticity after 28 days		UNI EN 13412	23.6 GPa
Capillary absorption coefficient		UNI EN 13057	0.43 kg*m ⁻² *h ^{-0.5}
Slipping resistance		UNI EN 13036-4	Dry: class II Wet: class III
Feature	Certifying body	Test method	Certified performance (**)
Impermeability in negative pressure (concrete structure Water/Concrete: 0.7)	IMM SA (Switzerland)	UNI EN 12390-8	7 Bar: no passage
Radon diffusion coefficient	CZECH TECHNICAL UNIVERSITY IN PRAGUE	ISO/TS 11665-13	1,4 E-10 m²/s

as well as Bi Mortar Plaster Seal Volteco or a product with equal or superior characteristics.

The technical data must be supported by test certification issued by an accredited official laboratory and / or be subjected to quality control according to ISO 9001.

The product must have the CE marking and be used according to the manufacturer's prescriptions.

For further details on the individual products and installation specifications, refer to the relevant technical data sheets which can be downloaded in the updated version on the website www.volteco.com.