

FIBROeRASO

Supply and installation of semi-rapid thixotropic mortar with a medium elastic modulus and controlled shrinkage, suitable for structural repair, smoothing and protection of reinforced concrete, with an excellent surface finish, applied in thicknesses between 1 and 40 mm depending on the type of use.

The product must be used for:

- Structural restoration to thickness and protective millimetre levelling of reinforced concrete structures such as pillars, beams and floors
- To repair exposed and prefabricated concrete walls
- Renovation of cornices and balcony risers
- Wall repair and finishing
- Restoration and structural reinforcement of large works such as viaducts and dams

The material must have the following characteristics:

EC Certification according to EN 1504-2

EC Certification according to EN 1504-3 - Class R4

Specification	Test method	Values
Water vapour permeability (equivalent thickness: Sd)	UNI EN 7783-2	Sd = 0.52 m
Flexural strength after 28 days	UNI EN 196-1	> 6.5 MPa
Compressive strength after 28 days	UNI EN 12190	50.7 MPa
Adhesion to the concrete	UNI EN 1542	2.17 MPa
Compressive modulus of elasticity after 28 days	UNI EN 13412	21.1 GPa
Resistance to carbonation	UNI EN 13295	fulfilled requisite
Capillary absorption coefficient	UNI EN 13057	0.35 kg*m ⁻² *h ^{-0.5}
Thermal compatibility Part 1 (adhesion after 50 un/freezing cycles)	UNI EN 13687-1	2.26 MPa

as well as FibroeRaso Volteco or a product with equal or superior characteristics.

The technical data must be supported by test certification issued by an accredited official laboratory and / or be subjected to quality control according to ISO 9001.

The product must have the CE marking and be used according to the manufacturer's prescriptions.

For further details on the individual products and installation specifications, refer to the relevant technical data sheets which can be downloaded in the updated version on the website www.volteco.com.