

PROFIX 20

Supply and installation of polysiloxane and acrylic microemulsion mixture capable of fixing the substrate and homogenising its absorption.

The product must be used for the preparation of mineral substrates, especially cementitious substrates (eg concrete, cement mortars, plasters) before applying smoothing compounds, coatings or finishes in general.

The material must have the following characteristics:

Specification	Values
Appearance	Whitish liquid
Specific weight	1 kg/l
Viscosity (+20 °C $\neq$ 2-100 rpm)	20 mPa x s
Workability time at +20 °C	30'
Dry residue	approx. 10%

as well as Profix 20 Volteco or a product with equal or superior characteristics.

The technical data must be supported by test certification issued by an accredited official laboratory and / or be subjected to quality control according to ISO 9001.

For further details on the individual products and installation specifications, refer to the relevant technical data sheets which can be downloaded in the updated version on the website www.volteco.com.